



Zwaluw Aqua-Silicone

Silicone for fresh and salt water aquaria



Product Description

Zwaluw Aqua-Silicone is an acetoxy silicone sealant which cures by reacting to moisture to form a durable elastic rubber.

Benefits

- Sealant and adhesive
- Non toxic for fish when fully cured
- For fresh and sea water aquaria

Applications

Zwaluw Aqua-Silicone was specifically developed for bonding and sealing full glass constructions as aquaria, terraria and showcases. The product has excellent adhesion to glass. For selecting the glass thickness of the aquarium we refer to DIN 32622.

Directions Of Use

A joint thickness between the sides and between the sides and the bottom, 1 to 2 mm is advised. Finish internal angles as a triangular joint of 3 to 5 mm depending on the water level. The sealant must be fully cured, curing time up to 1 week, before it can be transported or filled with water. After curing, rinse the aquarium several times with water before use. For further questions please contact our technical service.

Additional information

100 % modulus	DIN 53504 S2	0,50 N/mm ²
Application rate	@ Ø3 mm/6,3 bar	130 g/min
Application temperature		+5 °C to +40 °C
Base		Acetoxyl
Curing time	@ +23 °C/50% RH	2 mm/24 hours
Density	ISO 1183-1	1,03 g/ml
Elongation at break	DIN 53504 S2	600%
Flow	ISO 7390	< 2 mm
Frost resistance during transportation		Up to -15 °C
Joint movement		25%
Shorea hardness	DIN 53505	22
Skin formation	DBTM 16	5-6 minutes @ +23 °C/50% RH
Temperature resistance		-40 °C to +180 °C
Tensile strength	DIN 53504 S2	1,80 N/mm ²

These are typical values

Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable for aquaria larger than 1000 litres and/or higher than 60cm
- When gluing glass to glass miniscule air bubbles may still be visible after curing

Surface Preparations and Finishing

Application temperature: +5 °C to +40 °C (applies to environment and substrates). All substrates must be solid, clean, dry, and free from grease and dust. Clean substrates with Zwaluw Cleaner. Zwaluw Aqua-Silicone adheres perfectly without the use of a primer to most non porous substrates, like glass, painted wood, ceramic



Den Braven

Better
results
through
Knowledge

Technical Data Sheet

Zwaluw Aqua-Silicone

Silicone for fresh and salt water aquaria

and enameled. Always test adhesion prior to application. Use Zwaluw Finisher to smooth the joint.

Paintability

Zwaluw Aqua-Silicone is not paintable.

Cleaning

Uncured material and tools can be cleaned by using Zwaluw Cleaner. Cured material can only be removed mechanically. Hands can be cleaned with Zwaluw Wipes.

Colour(s)

- Transparent

Packaging

- Cartridge

For product specifications, please refer to the Product Detail Page

Shelf Life

In unopened original packaging between +5°C and +25°C, shelf life up to 24 months from production date, stored in a dry place.

Certifications

	A+ French VOC Regulation
--	--------------------------

Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via the Den Braven websites.

Warranty & Guarantee

Den Braven warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Den Braven. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Den Braven's written consent. The technical information in this document serves as an indication and is non-exhaustive. Den Braven is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Den Braven reserves the right to amend the wording of this document. Den Braven cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.