



Technical Data Sheet

Product	HMMB05D SheenSeries		
Description	Water-based clear self sealers		
Color	Clear		
Woods / Substrates for which the product is suitable	Walnut		
	Beech		
	Oak		
Chemical-physical Properties			
CODE	Density (Kg/l)	Density (lb/US gal)	Solid content %
HMMB05D	1,039 ± 0,030	8,7 ± 0,3	28,0 ± 2
HMMB052	1,039 ± 0,030	8,7 ± 0,3	28,0 ± 2
HMMB053	1,040 ± 0,030	8,7 ± 0,3	28,0 ± 2
HMMB054	1,040 ± 0,030	8,7 ± 0,3	28,0 ± 2
HMMB056	1,045 ± 0,030	8,7 ± 0,3	28,0 ± 2
	Viscosity (EN ISO 2431) ISO 3 cup		86 ± 5
USAGE INDICATIONS			
The product, after careful mixing, is ready to use			
READY TO USE PRODUCT PROPERTIES (AVERAGE)			
Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)	
		applied micron: 150	
		Wet Mils: 5,9	
	HMMB05D	Sheen 60 ± 4	
	HMMB052	Sheen 50 ± 3	
	HMMB053	Sheen 30 ± 2	
	HMMB054	Sheen 20 ± 2	
HMMB056	Sheen 10 ± 1		
Application	Quantities		
	Brush	gr/m ² min-max:	60 - 80
		Wet Mils min-max	2,3 - 3,0
	Manual roller	gr/m ² min-max:	60 - 80
Wet Mils min-max		2,3 - 3,0	

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilvacoatings.com



PRODUCT PROPERTIES AFTER APPLICATION		
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	96 h
	Dust free	50 min
	Touch dry	90 min
	Hard dry	5 h
	Sandable after (time)	4 h
	Overcoatability time	8 h
	Overcoatability time between layers	4-6 h
	Maximum time between layers without sanding	2-4 h
Shelf life	12 months after production	
SPECIFIC WARNINGS	<p>Sheen levels indicated in TDS are to be considered on the complete coating cycle</p> <p>If required, thin with water up to 5% (maximum)</p>	

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
 - tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
 codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
 ilva@ivmchemicals.com - www.ilvacoatings.com



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by quality and the preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.

On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- Water-based products are particularly sensitive to storage conditions: temperatures below 5 °C / 41°F and above 35 °C / 95°F may affect the product, characteristics, making it unusable. For this reason, a water-based product should be stored indoors at temperatures not below 5 °C / 41°F and not above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30 °C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 2016-07

Rev.: 1

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3
- tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. € 10.000.000
codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157
ilva@ivmchemicals.com - www.ilvacoatings.com